

Technical Data Sheet

Species	European Oak
Finish	Prefinished. Treffert – UV water based matte lacquer
Board Size	600mm × 120mm × 14/3mm
Locking System	Tongue & Groove
M2 per Carton	1.44
Surface	Light Wire Brush
Edges	Micro bevel on all 4 sides.
Boards per Carton	20 Boards, 10 Lefts, 10 Rights
Grade	ABC
Substrate	Eucalypt ply with a bottom layer of birch.
Underfloor Heating	Up to 26°C (surface temperature of subfloor not desired temperature of the room)
Installation Method	Direct Stick
Carton Weight	Approx 15kg.
Wet Slip - AS/NZS 4586-2013 Appendix A “Slip resistance classification of new pedestrian surface materials – Wet Pendulum Test Method” using a specified rubber Slider 96.	38 (P3)
Dry Slip - AS/NZS 4586-2013 Appendix B “Slip resistance classification of new pedestrian surface materials – Dry Floor Friction Test Method” using Slider 96	0.57 (D0)
Fire - AS(ISO) 9239-1:2003 Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a Radiant Heat Source.	Critical Heat Flux/Critical Radiant Flux* (3.3 kW/m ²)