

Technical Data Sheet

Species	European Oak
Finish	Prefinished. Treffert – UV water based matte lacquer
Board Size	189mm × 1860mm × 14/3mm
Locking System	Tongue & Groove
M2 per carton	2.11
Surface	Light wire brush
Edges	Micro bevel on all 4 sides.
Boards per carton	6 rows per carton with 2 nested rows per carton with a maximum of 2 pieces per row.
Grade	ABCD
Substrate	Eucalypt ply with a bottom layer of birch.
Underfloor heating	Up to 26°C (surface temperature of subfloor not desired temperature of the room)
Installation method	Floating, full glue, secret nail.
Carton weight	Approx 21kg.
Wet Slip - AS/NZS 4586-2013 Appendix A “Slip resistance classification of new pedestrian surface materials – Wet Pendulum Test Method” using a specified rubber Slider 96.	38 (P3)
Dry Slip - AS/NZS 4586-2013 Appendix B “Slip resistance classification of new pedestrian surface materials – Dry Floor Friction Test Method” using Slider 96	0.57 (D0)
Fire - AS(ISO) 9239-1:2003 Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a Radiant Heat Source.	Critical Heat Flux/Critical Radiant Flux* (3.3 kW/m2)

To be read in accordance with the Paramount Oak Flooring – Warranty and Paramount Native Flooring – Floating Floor Installation and Maintenance Guidelines.

Please note this Technical Data Sheet was written by Elite wooden floors All information above is correct and relevant at the time of writing and publishing this document. The company reserves the right to change the specifications of this product at any time without prior notice.